

STEPS TO WIN



kimpur
KIMTEKS POLYURETHANE

kim FOOT

FOOTWEAR SYSTEMS

— Kimfoot AA 09000 // Crosskim AA 39900 // İzokim AA 034

[in](#) [@](#) [f](#) / Kimpurglobal
www.kimpur.com

The comfort and lightness of sports shoes can have the power that will have an impact on your entire performance.

Kimfoot® sports shoe sole systems that increase the shoe comfort are three-component, low-density, polyester-based systems, which makes a difference with their advantages.

- High Flex Resistance
- Very Low Density
- Shiny Skin Appearance
- Short Demolding Time
- High Flowability

Kimfoot AA 09000 + Crosskim AA 39900 + İzokim AA 034

	UNIT	VALUE	METHOD
Recommended Density	kg/m ³	380-420	ISO 845
Hardness	ShA	45±5	DIN ISO 7619-1
Flexual Strenght - 14 °C		>30000	TS EN ISO 17707
Elongation	%	550	DIN 53504
Compression Set	%	35	TS EN ISO 1856
Tear Resistance	N/mm	7	DIN ISO 34-1

Measured values were obtained from tests made on samples prepared under laboratory conditions.

TURKEY'S POLYURETHANE SYSTEM HOUSE

SINCE
1983

2018 TÜRKİYE NİN İLK 1000 İHRACATÇI FİRMASI
TOP 1000 EXPORTERS OF TURKEY

Turkey's top
500
industrial enterprises

PRODUCTION CAPACITY
110.000
TONS



www.kimpur.com



KİMTEKS POLİÜRETAN SANAYİ VE TİCARET A.Ş.

HEAD OFFICE:

Emniyet Evleri Mah. Eski Büyükdere
Cad. Sapphire Plz. No: 1/4 Kat: 19 D: 01
Kağıthane 34415 İstanbul TÜRKİYE
Tel: +90 212 809 15 50
Fax: +90 212 809 15 49

GEBZE FACTORY:

Gebze Plastikçiler Organize
Sanayi Bölgesi 7. Cadde No: 43
41400 Gebze Kocaeli TÜRKİYE
Tel: +90 262 751 44 71
Fax: +90 262 751 02 57

GAZİANTEP:

Küçük Sanayi Sitesi B Blok
63 Nolu Cadde No:16
Şehitkamil Gaziantep TÜRKİYE
Tel: +90 342 325 57 97
Fax: +90 342 325 57 97